

# PanSPERSE 900

## Zero VOC\* Aqueous Pigment Dispersing Additive

PanSPERSE 900 is an environmentally friendly aqueous dispersing agent effective with most organic and inorganic pigments. PanSPERSE 900 is solvent free and contains no alkylphenolethoxylates. Colorants made with PanSPERSE 900 are compatible with most waterborne coatings and inks.

## Suggested Applications

PanSPERSE 900 is intended for use in making highly concentrated pigment dispersions for coloring conventional, low and zero VOC aqueous coatings and inks. Dispersions made with PanSPERSE 900 have exceptionally wide compatibility and can be used in both ambient cured and baking finishes. PanSPERSE 900 can also be used to correct problems of floating and flocculation in finished coatings and inks. PanSPERSE 900 has little or no effect on exterior durability. It can be used in exterior architectural paints, high performance maintenance coatings, transportation finishes, and other applications subject to extreme weathering.

## Usage Levels

In the manufacture of concentrated pigment dispersions, PanSPERSE 900 should initially be evaluated at a starting point of approximately 8-10% by weight on total formula. The level can be adjusted as needed for optimum pigment loading and viscosity. In most cases, no other surface active material, additive or stabilizing agent will be needed. Post addition of 1-2% by weight is often adequate to significantly reduce or eliminate floating, flocculation or similar defects resulting from minor incompatibilities within the coating.



## Typical Values

COMPOSITION % BY WEIGHT		COMPOSITION % BY VOLUME		DENSITY		VOC	
Surfactant Solids	Water	Surfactant Solids	Water	lb/gal	Sp. Gr.	lb/gal	Gr/L
75.5	24.5	73.3	26.9	9.11	1.09	<0.05	<5

\*VOC is below that level which can be determined accurately by EPA Test Method 24.

## Suggested Starting Formulas

Phthalo Blue, C.I. Pigment Blue 15:2	
Pigment	35.0
PanSPERSE 900	8.5
Water	33.0
Ammonium Hydroxide	0.5
<i>Mill in Small media mill to 7+ Hegman</i>	
Water	23.0
	100.0

Naphthol Red, Pigment C.I. Red 170	
Pigment	30.0
PanSPERSE 900	9.0
Water	44.5
Ammonium Hydroxide	0.5
<i>Mill in Small media mill to 7+ Hegman</i>	
Water	16.0
	100.0

Yellow Oxide, C.I. Pigment Yellow 42	
Pigment	59.4
PanSPERSE 900	11.0
Water	20.8
Ammonium Hydroxide	0.5
<i>Mill in Small media mill to 7+ Hegman</i>	
Water	8.3
	100.0

Tinting Black, C.I. Pigment Black 7	
Pigment	35.0
PanSPERSE 900	10.3
Water	33.0
Ammonium Hydroxide	0.5
<i>Mill in Small media mill to 7+ Hegman</i>	
Water	21.2
	100.0



Your guarantee of manufactured excellence.