

8019 Ohio River Blvd Newell, WV 26050 USA Ph: 304-387-1200 Fax: 304-387-1289 siliconesRFQ@bellofram.com

# 5404-NSF NSF/ANSI 51 CERTIFIED MEDIUM FIRM SILICONE SPONGE EXTRUDED PRODUCTS

### **DESCRIPTION**

Bellofram Silicones 5404-NSF is a medium firm density FDA Compliant and NSF/ANSI 51 Certified closed cell silicone sponge elastomer product, available in both standard and custom extruded profiles. Our sponge materials are designed for applications in which low compressive force and distance are required for sealing, as well as where temperature resistance is important.

Contact us at siliconesRFQ@bellofram.com to request a free product sample or quotation.



## **FEATURES**

- Handles temperature extremes
- · Excellent gasketing material
- · Low closure force
- Very low compression set
- Ultraviolet ray (UV) resistant
- Ozone resistant

### **MATERIAL SPECIFICATIONS**

- ASTM D-1056 2D4
- AMS 3196F
- 21CFR177.2600
- NSF/ANSI 51 Certified

## TYPICAL PHYSICAL PROPERTIES

| PROPERTY                                | TEST METHOD | SPECIFICATION   |
|---|-------------|-----------------|
| Compression Deflection                  | ASTM D-1056 | 13 to 17 psi    |
| Heat Age (22 Hours @ +150°C)            | ASTM D-1056 | +/-5% Change    |
| Water Absorption                        | ASTM D-1056 | 10%             |
| Compression Set (22 Hours @ +100°C)     | ASTM D-1056 | 46%             |
| Low-Temperature Flex (5 Hours @ -55°C)  | ASTM D-1056 | PASS            |
| Flammability                            | FMVSS 302   | PASS            |
| Temperature Resistance (Continuous)(°F) |             | -85° to + 400°F |

Data noted above is based on laboratory tests and should be used as a reference only. Further information and additional specifications are available upon request. Tests, claims, representations, and descriptions regarding flammability are based on standard laboratory tests, and they may not be reliable for determining, evaluating, predicting, or describing the flammability or burning characteristics under actual fire conditions, whenever used alone or in combination with other products. Accordingly, each potential user should make an individual determination whether the flammability or burning characteristics of the product are suitable for the purpose intended by the user.